

## **Heidelberg Materials**

## **Tanzania Portland Cement Public Limited Company**

P.O.Box 1950,Dar es Salaam-Tanzania

Telephone: +255 746 810930 Fax: +255 746 810931 www.twigacement.com

## MONTHLY CERTIFICATE OF CHEMICAL AND PHYSICAL TESTS TWIGA EXTRA, CEM II/B-L CLASS 32.5 R AUGUST, 2024

Sampled and tested in accordance with the requirements of the Tanzanian Bureau of Standards

TZS 727-1/EAS 18-1

	CHEMICA	L TEST RESULT	rs
Test	Unit	Test results monthly average	Specified requirements
Loss on ignition	[%]	14.2	No Requirement
Insoluble Residue	[%]	1.21	Less than 5.0%
CaO	[%]	55.1	No Requirement
SiO <sub>2</sub>	[%]	18.6	No Requirement
CaO/SiO <sub>2</sub>	[-]	2.96	Not less than 2.0%
Al <sub>2</sub> O <sub>3</sub>	[%]	4.71	No Requirement
Fe <sub>2</sub> O <sub>3</sub>	[%]	2.99	No Requirement
MgO	[%]	0.98	Not more than 5.0%
SO <sub>3</sub>	[%]	2.51	Less than 3.5%
K₂O	[%]	0.41	No Requirement
Na <sub>2</sub> O	[%]	0.18	No Requirement
P <sub>2</sub> O <sub>5</sub>	[%]	0.40	No Requirement
ΓiO <sub>2</sub>	[%]	0.49	No Requirement
MnO	[%]	0.07	No Requirement
Na <sub>2</sub> O+0.658K <sub>2</sub> O)	[%]	0.45	No Requirement
Cl	[%]	0.002	Less than 0.10%
	PHYSICAL	TEST RESULT	S
Density	[kg/m <sup>3</sup> ]	3100	No requirement
Specific Surface (Blaine)	[m²/kg]	460	No Requirement
Sieving Residue on 45 mic.	[%]	11.9	No Requirement
nitial setting time	[minutes]	156	Not less than 75 minutes
Soundness (expansion)	[mm.]	1.0	Not more than 10 mm.
Compressive strength 2 days	[MPa]	13.0	More than 10 MPa.
Compressive strength 28 days*	[MPa]	34.5	Between 32.5 and 52.5 MPa

Remarks: \*The 28 days strength is the average of previous month.

Wazo Hill, 2024/09/04th

Quality Control Manager

Board Directors: Hakan Gurdal (Turkish) Alfonso Velez (Spanish) Francesco Brambilla (Italian) Plant Manager

Ruth Zaipuna (Tanzanian) Gary Whitehead (British) Oswald Urassa (Tanzanian) Commercial Director