

## Heidelberg Materials

Tanzania Portland Cement Public Limited Company
P.O.Box 1950,Dar es Salaam-Tanzania
Telephone: +255 746 810930

Fax: +255 746 810931 www.twigacement.com

## MONTHLY CERTIFICATE OF CHEMICAL & PHYSICAL TESTS TWIGA PLUS, CEM II/B-M CLASS 42.5 N JULY, 2024

Sampled and tested in accordance with the requirements of the Tanzanian Bureau of Standards

## TZS 727-1/EAS 18-1

	CHEMICAL TI	EST RESULTS	
Test	Unit	Test results	Specified requirements
Loss on Ignition	[%]	8.18	No requirement
Insoluble Residues	[%]	1.20	Less than 5.0%
CaO	[%]	56.3	No requirement
SiO <sub>2</sub>	[%]	20.2	No requirement
CaO/SiO <sub>2</sub>	[-]	2.78	Not less than 2.0%
Al <sub>2</sub> O <sub>3</sub>	[%]	5.03	No requirement
Fe <sub>2</sub> O <sub>3</sub>	[%]	3.26	No requirement
MgO	[%]	1.49	Not more than 5.0%
SO <sub>3</sub>	[%]	2.45	Less than 3.5%
K <sub>2</sub> O	[%]	0.40	No requirement
Na <sub>2</sub> O	[%]	0.23	No requirement
P <sub>2</sub> O <sub>5</sub>	[%]	0.46	No requirement
TiO <sub>2</sub>	[%]	0.79	No requirement
MnO	[%]	0.08	No requirement
(Na <sub>2</sub> O+ 0.658 K <sub>2</sub> O)	[%]	0.49	No requirement
Cl <sup>-</sup>	[%]	0.001	Less than 0.10%
	PHYSICAL TE	ST RESULTS	
Density	[kg/m3]	3100	No requirement
Specific Surface (Blaine)	[m <sup>2</sup> /kg]	451	No requirement
Sieving Residue on 45 mic. mesh	[%]	8.6	No requirement
Initial Setting Time	[Minutes]	173	Not less than 60 minutes
Soundness (Expansion)	[mm]	1.0	Not more than 10.0 mm
Compressive Strength 2 days	[MPa]	17.8	More than 10.0 MPa
Compressive Strength 28* *days*	[MPa]	44.2	Between 42.5 and 62.5 Mpa

Remarks: \* The 28 days strength is the average of previous month.

Wazo Hill, 2024/08/05th

Quality Control Manager

Plant Manager

4 - Commercial Director

Board Directors Hakan Gurdal (Turkish) Alfonso Vellez (Spanish) Francusco Brandalla (Italian

Ruft Zaguna (Tanzanan) Gary Whitchran (British) Oswald trassa (Tarzonan)