

Heidelberg Materials

Tanzania Portland Cement Public Limited Company P.O.Box 1950, Dar es Salaam-Tanzania

Telephone: +255-746 810 930 Fax: +255-746 810 931

Info@twigacement.com www.twigacement.com

MONTHLY CERTIFICATE OF CHEMICAL AND PHYSICAL TESTS TWIGA ORDINARY, CEM I CLASS 42.5 N

SEPTEMBER,2024

Sampled and tested in accordance with the requirements of the Tanzanian Bureau of Standards

TZS 727-1/EAS 18-1. Equivalent to EN 197-1

	CHEMIC	AL TEST RESULTS	
Test	Unit	Test results monthly average	Specified requirements
Loss on ignition	[%]	4.44	Less than 5.0%
Insoluble residue	[%]	1.00	Less than 5.0%
CaO	[%]	60.2	No Requirement
SiO ₂	[%]	20.9	No Requirement
CaO/SiO ₂	[-]	2.88	Not less than 2.0%
Al ₂ O ₃	[%]	4.85	No Requirement
Fe ₂ O ₃	[%]	3.29	No Requirement
MgO	[%]	0.82	Not more than 5.0%
SO_3	[%]	2.50	Less than 3.5%
K ₂ O	[%]	0.37	No Requirement
Na ₂ O	[%]	0.14	No Requirement
P ₂ O ₅	[%]	0.36	No Requirement
TiO ₂	[%]	0.46	No Requirement
MnO	[%]	0.05	No Requirement
(Na ₂ O+0.658K ₂ O)	[%]	0.39	No Requirement
Cl ⁻	[%]	0.001	Less than 0.10%
	PHYSICA	AL TEST RESULTS	
Density	[kg/m³]	3000	No requirement
Specific Surface (Blaine)	[m²/kg]	357	No Requirement
Sieving Residue on 45 mic.	[%]	14.2	No Requirement
Initial setting time	[minutes]	136	Not less than 60 minutes
Soundness (expansion)	[mm.]	1.0	Not more than 10 mm.
Compressive strength 2 days	[MPa]	19.1	More than 10 MPa.
Compressive strength 28 days*	[MPa]	50.1	Between 42.5 and 62.5 MPa

Remarks: *The 28 days strength is the average of previous month.

Wazo Hill, 2024/10/04th

Board Directors: Hakan Gurdal (Turkish)

Alfonso Velez (Spanish)

Francesco Brambilla (Italian)

Quality Contro Manager

Plant Manager

Ruth Zaipuna (Tanzanian) Gary Whitehead (British) Oswald Urassa (Tanzanian) Commercial Director